

**RESIFLOW® L-3075
FLOW CONTROL AGENT
FOR THE COATINGS INDUSTRY**

www.estron.com



THE EDGE OF INNOVATION

GENERAL DESCRIPTION

Resiflow® L-3075 is a specialty acrylic polymer additive provided at 75% solids in Solvent 100 (Hi-Sol 10) for use in coil coating systems. Resiflow® L-3075 affords excellent air release, improved film characteristics, and resistance to dirt-pick up. The recommended level of usage is between 0.2-2.0% based on coating resin weight. As with any additive, laboratory evaluation should be carried out for each formulation to determine the best processing method and optimum concentration.

TYPICAL PROPERTIES*

Appearance	Clear Liquid
Gardner Color	3 maximum
Specific Gravity (25/25)	0.98 – 1.02
Gardner Viscosity	S – W
Non-Volatile, weight %	73 – 77%
Acid value, mg KOH / gram	5 maximum

* Not to be used for specification purposes

REGULATORY LISTINGS

The components in this material are either listed or exempt from listing due to polymer exemption criteria for the following chemical listing inventories: EINECS (Europe), TSCA (USA)

PACKAGING (NET WEIGHT)

44 lb. / 20.0 kg in steel pail
440 lb. / 199.6 kg in steel drum

PRODUCT AVAILABILITY

This product is commercially available, but may require lead time.

STORAGE AND HANDLING

Keep container tightly closed and store in a dry, well ventilated area away from extreme heat, open flame or sources of ignition. Store locked up. Shelf life of unopened containers is 1 year from date of shipment. See SDS for additional information.

CONTACT INFORMATION

807 N. Main Street
P.O. Box 127
Calvert City, KY 42029 USA

(270) 395-4195 PHONE
(270) 395-5070 FAX

Revision Date: October 9, 2017

TDS Revised by: A. Chizhikova

TDS Approved by: F. Allen